





Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

- **Drying time (at 20°C, 50% relative air humidity):**  
can be sanded after approx. 40 minutes
- **Flash point:**  
approx. 33°C (resin); not applicable for hardener
- **Density at 20°C:**  
resin 1.2 g/cm<sup>3</sup>  
hardener 1.15 g/cm<sup>3</sup>
- **Addition of hardener:** 2 - 4 % (optimal mixture 2,5 %)
- **Temperature resistance of the cured material:** 120°C
- **Storage stability:**  
18 months if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%) in the unopened original container. Protect from direct sunlight, frost and humidity.
- **Packing:**  
small ring tins; hardener: plastic tubes

## Environment and labelling

**Environmentally sound:** The products of Chamäleon are 100% free of heavy metals. The caps and packagings are made of recyclable material.

**Disposal:** Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

**Marking/Labelling:** All products made by Chamäleon comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:  
e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)  
See information on safety in Safety Data Sheet.*