



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon-produktion.de
http: //www.chamaeleon-produktion.de

ТЕХНИЧЕСКИ ЛИСТ

ШАГРЕН НА ВОДНА ОСНОВА

Код: **37245**

Обща характеристика: Водоразтворимият шагрен е водоразтворима и екологична боя за защита от удари от камъчета със звукопоглъщащи свойства. Подходящ и като изолационен грунд с гладка повърхност.

Процес на боядисване:

Цвят: черен

Втвърдител: -

Разреждане: готов за употреба, при необходимост може да се добавят 10% вода

Вискозитет при пръскане **4 mm DIN**: тиксотропичен

Процес на нанасяне:


Параметри	Налягане	Дюза
Конв. пистолет	2.0 - 2.5 bar	1.3 - 1.5 mm
HVLP	2.0 - 2.2 bar	1.3 - 1.5 mm
Airmix / Airless	100 - 120	0.33 - 0.50 mm
UBS	4 - 6	5 - 10 mm

Слоеве	Деб. на сухия филм	Разход
2	100 - 300 µm	2.5 - 5 m ² /l

Време за изпарение	Между слоевете	Преди изпичане
	5 - 8 minutes	10 - 15 minutes

Условия на работа:

80% - +10 °C

 Drying		Dust free	Set to touch	Ready for assembly	Recoatible
---	--	-----------	--------------	--------------------	------------



Chamäleon GmbH
 Rudolf-Diesel-Straße, 8a
 69115 Heidelberg-Germany
 Tel.: +49-(0)-6221 520440
 Fax: +49-(0)-6221 520449
 E-mail: info@chamaeleon-produktion.de
 http: //www.chamaeleon-produktion.de

Object temperature	20 °C	25 - 30 minutes	30 - 35 minutes	24 hours	60 minutes
Object temperature	60 °C		10 - 15 minutes	1 hour	15 - 20 minutes

VOC regulation

EU limit value: Category B/e 840 g/l

This product contains max. 100 g/l.

Processing tips

The substrate must be dry, clean and free from grease and rust. Pre-treat iron and steel surfaces to protect against corrosion. Sand slightly aluminium surfaces and old paintwork. The underbody must be cleaned thoroughly. It must be dry, free from dust, grease, oil and rust. Old non-adherent underbody coating must be removed. Mask beforehand motor, exhaust pipes, stub axles, cardan shaft and brake system as they must not be sprayed!

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding safety data sheet.