





Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

Before use, carefully read the directions on the packaging and act accordingly.

**Pre Treatment:**

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

**Treatment:**

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimeter.

Apply the filler in several thin layers. Before applying the next layer, again shake the aerosol.

**After use:**

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:  
e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)*



*See information on safety in Safety Data Sheet.*

Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>