

## ТЕХНИЧЕСКА ХАРАКТЕРИСТИКА

### БЪРЗ ОЛЕКОТЕН ФИН КИТ

Код	<b>15525</b>
Цвят:	Зелен
Приложение:	Авторепаратурен продукт/ Кит/ Основа
Обща характеристика:	Самоизравняващ, олекотен 2К полиестерен фин кит. Използва се за запълване на малки пори или за изравняване на малки неравности. Има интегрирана индикация за живот на сместа: Бързият олекотен фин кит сменя цвета си от зелено в бежово по време на фазата на втвърдяване, осигурявайки визуална проверка на процеса на съхнене. След изсъхване Chamäleon Fast Finish има гладка, лъскава и затворена повърхност и се характеризира с лекота при шлайфане. Отлична адхезия към желязо, стомана, алуминий, цинковани основи, стъклопласт и дърво.

#### Процес на подготовка:

Втвърдител: Втвърдител Р  
Смесване: добавят се 3% втвърдител  
Живот на сместа при 20 °С: 3 - 4 мин.

#### Условия на работа:

Моля, използвайте само в подходяща вентилирана среда с достатъчно свеж въздух. Температурата на обработка трябва да бъде минимум +10 °С и макс. влажността на въздуха не трябва да надвишава 80%. Шпакловката на полиестерна основа вече не се втвърдява при температура под +10 °С.

Съхнене	Шлайфане
Температура на обекта <b>20 °С</b>	15 - 20 мин.
Температура на обекта <b>60 °С</b>	5 - 10 мин.

:

The substrate must be clean, dry and free from grease. Sand surfaces slightly. Remove not cured old

paintwork and priming coats. Do not apply on thermoplastic or acid products (wash-primer). Mix well the putty material with the hardener. Do not use more than 3% of hardener P! Under- or overdosage of hardener may cause spotting in the finishing paint layer.

Clean and degrease the whole surface to be painted before every operation. De-rust defective spots to bare metal and dry sand with sanding paper P 80 / 150. After drying, use sanding paper P 150 / 240 for dry sanding. Sand the entire surface with dry sand paper P 240 / 360 to a matt finish before applying primer. In case of filling work on non-ferrous metals (e.g. aluminium, zinc surfaces) it is possible to apply a priming coat to ensure an optimal adhesion before applying the putty. Do not overcoat without having isolated the surface with 1K or 2K filler. Fast finish putty can only be dry sanded.

### **VOC regulation:**

EU limit value: Category B/b 250 g/l

This product contains max. 10 g/l.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under:

e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)

For safety information, please refer to the corresponding safety data sheet.